

1800



PATCO® 1800 Flame Retardant Galley Tape


APPLICATIONS

- Aircraft corrosion inhibitor.
- Aircraft wetseal applications in main cabin areas such as galleys, lavatories, entryways, and other areas susceptible to moisture.
- Meets FAR 25.853(a) Appendix F for Interior Aircraft Use

FEATURES & BENEFITS

- Tough, conformable, and moisture resistant.
- · Permanent and flame retardant.
- · Allows wide width usage.
- Helps prevent corrosion on floor structures.
- Will not delaminate. Meets FAR requirements.
- · Compatible with most sealants.
- Fast applications.
- · Can be die-cut to various shapes.

CONSTRUCTION



PRODUCT DESCRIPTION

Single-Coated w/Liner Construction Backing:

· Polyvinyl Chloride

Adhesive:

Acrylic

Liner:

· 53# Coated Kraft Paper

Colors:

Black

TEST DATA

Test	Typical Value	Typical Value (Metric)	Test Method	
Total Thickness	10 mils	0.254 mm	PSTC-133	
Substrate Thickness	8.5 mils	0.216 mm	PSTC-133	
Adhesion to Steel	50 oz./in.	0.547 N/mm	ASTM D-3330	
Tensile Strength	25 lb./in.	4.378 N/mm	ASTM D-3759	
Elongation (%)	200 %			
Application Temperature Range	50°F to 120°F	10°C to 49°	10°C to 49°C	
Operating Temperature Range	-40°F to 200°F	-40°C to 93°	-40°C to 93°C	

The information presented hereinwas prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Frankin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchase or user, as the case may be, will independently determine that the product is subble for the included use, and that such use completes with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.



^{**}Recommended storage conditions: 40-60% Humidity, 60 °F - 80 °F